

VAC-PAK[®] HS8171PS

Adhesive tape

Ideally suited to masking applications

Features and Benefits

- High temperature nylon tape with a pressure sensitive, rubber-base adhesive on one side
- Designed to strip cleanly from the part during masking operations in high temperature/pressure applications
- High elongation properties provide a high degree of conformability
- Rubber based adhesive allows for use on parts where subsequent painting or bonding is necessary
- High stretch and thinness offer excellent conformability and clean, sharp edges

PROPERTIES

| | | |
|--------------------------|--------|----------|
| Maximum cure temperature | 204°C | 400°F |
| Color | Green | |
| Adhesive | Rubber | |
| Carrier | Nylon | |
| Total thickness | 88µm | 0.0035in |
| Adhesive thickness | 38µm | 0.0015in |
| Tape thickness | 50µm | 0.002in |
| Elongation at break | 500% | |

AVAILABILITY

| | | |
|-----------------|------------------------------|-----------------|
| Standard width | 19.05, 25.4, 50.8 and 76.2mm | ¾, 1, 2 and 3in |
| Standard length | 65.8m | 72yd |

STORAGE

No special storage conditions.

HEALTH & SAFETY

Please refer to the product MSDS for safe handling, personal protective equipment recommendations and disposal considerations.

DISCLAIMER: The data and information provided in this document have been obtained from carefully controlled samples and are considered to be representative of the product described. Solvay does not express or imply any guarantee or warranty of any kind including, but not limited to, the accuracy, the completeness or the relevance of the data and information set out herein. Because the properties of this product can be significantly affected by the fabrication and testing techniques employed, and since Solvay does not control the conditions under which its products are tested and used, Solvay cannot guarantee the properties provided will be obtained with other processes and equipment. No guarantee or warranty is provided if the product is adapted for a specific use or purpose. Solvay declines any liability with respect to the use made by any third party of the data and information contained herein. Solvay has the right to change any data or information when deemed appropriate. All trademarks are the property of their respective owners. ©2017, Solvay. All rights reserved.

Solvay
Composite Materials HQ
4500 McGinnis Ferry Rd
Alpharetta, GA 30005-3914 USA

21 March 2013

