



352

Aramid and High Performance Fabrics

Product Data

12/3/07

STYLE 352

Type of Yarns	Warp Yarn:	Kevlar®, K-49 1140 denier	
	Fill Yarn:	Kevlar®, K-49 1140 denier	
Fabric Weight, Dry	5.1	(oz/sq. yd)	+/- 4%
	173	(g/sq. m)	+/- 4%
Weave Style	Plain		

CONSTRUCTION

Nominal Construction Yarns/inch	Warp Count:	17	+/- 1
	Fill Count:	17	+/- 1
Fabric Thickness	10.0	(mils)	+/- 0.5 mil
	0.25	(mm)	+/- 0.05 mm
Breaking Strength, (Fabric)	Warp	624 (lbf/in)	
	Filling	643 (lbf/in)	

Markets

Safety and Personal Protection

Applications

Aerospace / Composite

IMPORTANT

All information is believed to be accurate but is given without acceptance of liability. Users should make their own assessment of the suitability of any product for the purpose required. All sales are made subject to our standard terms of sales which include limitations on liability and other important terms. The fabric style listed may not be available from inventory, and minimum order quantities may apply. Kevlar® is a Registered Trademark of DuPont.



2200 S. Murray Ave.
Anderson, S.C. 29624
Tel (864) 260-3286
Fax (864) 260-6581