

NOROX[®] MEKP-9

Methyl ethyl ketone peroxide
CAS#1338-23-4
Liquid mixture

Description

NOROX MEKP-9 is a methyl ethyl ketone peroxide in phlegmatizer for the curing of unsaturated polyester resins at ambient temperature in combination with cobalt accelerators. NOROX[®] MEKP-9 gives consistent room temperature performance with both resins and gelcoats. NOROX[®] MEKP-9 is a reliable product of remarkable purity and is available globally. NOROX[®] MEKP-9 assures quality in almost every system.

Technical Data

Active oxygen content	9.0
Water content	1.2%
Appearance	Colourless and clear liquid
Specific Gravity at 20°C:	1.11 - 1.14
Flash point(Seta closed cup)	> 75°C (> 170 °F)
SADT:	65°C (149 °F)
Soluble in:	Oxygenated organic solvents
Slightly soluble in	Water
Storage temperature	Max 25°C (77 °F)

Application

NOROX[®] MEKP-9 is an excellent liquid general-purpose cure initiator for the room temperature cure of polyester resins. In this application it imparts medium to high exotherm characteristics to the cure.

NOROX[®] MEKP-9 is highly refined and substantially free of polar compounds such as water, hydrogen peroxide, glycols and methyl ethyl ketone. NOROX[®] MEKP-9 give therefore excellent performance as a curing agent for gelcoats, especially US formulated gelcoats.

Resin suppliers should be consulted for specific recommendations for individual resins.

NOROX[®] MEKP-9 gives slightly longer gel time than NOROX[®] KP-9. Depending on the working conditions, normal dosage level is 1 – 3% based on the resin.

Measurements

CURE CHARACTERISTICS

A reactivity test with an unsaturated polyester resin gave the following results:

Resin: Orthophthalic polyester Temperature: 21°C
Initiator %: 1.0 Accelerator%: 1%(1%cobalt)

Initiator	Gel time Min	Time to peak min	Peak exotherm temp °C
NOROX® MEKP-9	14	55	52
NOROX® MEKP-925	15	59	43
NOROX® KP-9	11	48	47

A curing test with a gelcoat gave the following results

Method: Thin film cure(500um, wet film) Temperature 23°C
Gelcoat: Low VOC ISO-NPG, white spray gelcoat
TTC: Tack-Free time Initiator %: 2.0

Initiator:	Gel time min	TTC min
NOROX® MEKP-9	25	110
NOROX®MEKP 925	28	108
NOROX® KP-9	19	113

PACKAGING, SHIPPING & AVAILABILITY

- The standard package sizes of NOROX® MEKP-9 are 4x8 lb and 44 lb (20 kg) polyethylene bottles.
- NOROX® MEKP-9 is available pre-dyed in 40 lb (20kg) bottles. Please see United Initiators, Inc. TDS for Peroxide Dye Concentrates.
- Classification – Please refer to the specific NOROX® MEKP-9 Safety Data Sheet (SDS) under section 14 & 15, shipping & regulatory information. **NOTE:** SDS's for all United Initiators, Inc. products may be requested by contacting the company.
- NOROX® MEKP-9 is available through a global network. Call United Initiators, Inc. for the name of the distributor in your area

This information and our application-technical advice – whether verbal, in writing or by way of trials – reflect our present state of knowledge based on internal tests with local raw materials. Their purpose is to inform interested parties about our products and their possible application. They should not be construed as guaranteeing specific product properties or their suitability for a particular application. Furthermore, the information does not contain complete instructions for use. Nor does it constitute a guarantee as to quality and durability. Changes due to technical progress and corporate advancement reserved. Any existing third-party copyrights are to be taken into account.

Application and use of our products based on our application-specific advice is beyond our control and sole responsibility of the user. The user is not released from the obligation of verifying the suitability and applicability as to the intended purpose.

United Initiators
EU
T: +49 89 74422 237
F: +49 89 74422 6237
cs-initiators.eu@united-in.com

United Initiators
Nafta
T: +1 800 231 2702
F: +1 440 323 0898
cs-initiators.nafta@united-in.com

United Initiators
China
T: +86 20 6131 1370
F: +86 139 2503 8952
cs-initiators.cn@united-in.com

United Initiators
Australia
T: +61 2 9316 0046
F: +61 2 9316 0034
cs-initiators.au@united-in.com

www.united-initiators.com