

SPECIFICATIONS

REK GHC/I

1" Graphite Honeycomb High Temperature

TEST RESULTS:

Peel Strength:

	Width In.	Machine Load Lbs.	Peel Strength In.-Lbs./3" Width
Thickside			
1	2.908	100	39.46
2	3.021	100	39.45
3	3.025	100	39.48
4	2.832	100	39.48
5	2.783	100	39.29
6	3.062	100	39.45
Mean			39.43
Std. Dev.			0.07

Flexural Strength:

	Width In.	Depth In.	Span In.	Flexural Strength Lbs./In. Width
Ambient				
1	3.074	1,090	20	316
2	3.001	1,090	20	283
3	3.057	1,090	20	281
4	2.865	1,103	20	269
5	3.088	1,081	20	277
Mean				285
Std. Dev.				18
6	2.869	1,092	20	127
7	2.847	1,083	20	175
8	2.836	1,080	20	106
9	2.766	1,093	20	90
10	2.708	1,090	20	130
Mean				126
Std. Dev.				32
Service Temp 400°				



42130 Mound Rd. Sterling Heights, Michigan 48314 (586) 739-8850 Fax: (586) 739-0750