

CRESTOMER[®] Advantage 60

Technical Data Sheet



Product Overview

Crestomer Advantage 60 is a structural adhesive that bonds a wide range of substrates with minimal surface preparation and lower odour than competitive materials. It has a white colour, with a geltime of 60 minutes and bonded parts are workable in 3 hours. Crestomer Advantage 60 is based on Scott Bader's innovative urethane acrylate technology and exhibits exceptional impact strength and toughness. Its excellent adhesion and gap filling capabilities offer great flexibility in design with significant time and cost savings.

Features and Benefits

Urethane acrylate base	▶	Excellent adhesion and high elongation at break
Excellent retention of toughness	▶	Highly thixotropic
Excellent fatigue and impact resistance	▶	Perfect gap filling solution
Non sag	▶	Application on vertical surfaces

Application Properties

Working Time	60 Minutes
Fixture Time ²	3.0 hours
Gap Filling	1 – 15 mm/ 0.04 - 0.6 inch
Colour change (over cure)	None
Recommended Application Temperature	18°C - 25°C/ 66°F - 77°F

Mechanical Properties

Tensile Strength ⁵	22 - 25 MPa
Tensile Modulus	400 - 600 MPa
Tensile Elongation	100 - 120%
Hardness	55 Shore D
Water Absorption	0.68%
Approvals	-


Liquid Properties

Product	Advantage 60
Viscosity ³	280,000 - 350,000 cP
Specific Gravity	1.15
Volatile Content	40 - 45%
Mixed Ratio ⁴ (by Volume)	10:1
Appearance	White paste
Shelf Life ⁵	12 months

Recommended Substrates

	Recommended Substrates (Lap Shear Strength MPa ⁶)	Non - Recommended Substrates
Metals	Stainless Steel Aluminium	-
Wood	Marine Ply Balsa	-
Composites	GRP/FRP Polyester Resin DCPD Vinyl Ester Epoxy	-

FRP to FRP Bond Strength



Surface Preparation

Crestomer Advantage 60 has excellent adhesion to FRP material provided that the surface has been maintained free of dust and grease. This can be guaranteed by the use of proprietary stripable cloths such as peel ply (without lubricant contaminates). If the laminate surface is more than three days old it is recommended that they are lightly abraded and wiped with acetone or styrene on a lint-free, clean cloth prior to bonding.

Application

Crestomer Advantage 60 is supplied ready to use in pre-packed 380ml co-axial cartridges with no hand mixing required. Crestomer Advantage 60 is supplied pre-accelerated and contains advantage catalyst within the cartridge. The mixer indicator system imparts a neutral, opaque white colour and this blends well in cosmetically sensitive applications.

For industrial/ commercial use only. The user must determine the suitability of a selected adhesive for a given substrate and application. Contact your local Scott Bader representative for questions or assistance with the selection of adhesives for your use. This product is intended for use by skilled individuals at their own risk. Recommendations contained herein are based on information we believe to be reliable. The properties and strength values are obtained under controlled conditions at the Scott Bader laboratory.

Storage and Shelf Life

Crestomer Advantage 60 should be stored internally in its original container. It is recommended that the storage temperature should be between 15°C and 20°C/ 60°F and 68°F. Cartridges should be opened only immediately prior to use. Products should never be frozen.

The shelf life for Crestomer products is defined from date of manufacture if stored as recommended. The expiry date is indicated on the product labels.

Packaging

Crestomer Advantage 60 is supplied in 380ml co-axial cartridges.

Health and Safety

See separate Material Safety Data Sheet.

1. Geltime measured with 100g mass of adhesive at 25°C/ 77°F.

2. Time taken at 23°C/ 73°F (ambient temperature) to achieve 1.4MPa strength in lap-shear tests according to BS ISO.

3. Measured using Brookfield Viscometer at 25°C/ 77°F.

4. Mix ratio based on cartridge dispensing, as supplied.

5. Shelf life defined from date of manufacture when stored as recommended.



© 2018 ScottBader Co Ltd, February 2018

Scott Bader UK

Wollaston, Wellingborough, Northants
NN29 7RL, UK

Tel: +44 (0)1933 666738

Email: enquiries@scottbader.com

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.