

EMC(T)600

【Product Description】

Composed of E-glass chopped strands bounded with unsaturated polyester binder.
 Application for hand lay-up.
 Compatible with unsaturated polyester resins and vinyl resins for manufacture of panel, boat hulls and other FRP parts.

【Characteristics】

Thickness steady and optimum stiffness.
 Excellent strands dispersion and outstanding bonding on double sides.
 Easy impregnation, good air-releasing performance and less resins consumption.
 Optimum wet out, excellent processibility, high abrasion and corrosion resistance
 Good mechanical properties

【Technical data】

Specification	Width (mm)	LOI %	Styrene solubility (S)	Moisture (%)	Process
EMC (T) 600	100-3000	3.4+/-1.5	≤40	≤0.20	Hand lay-up

Notes:1. Individualized specification is available as per customer's request.
 2. this data sheet herein above is provided for information purposes only and CTG reserves the right to modify it without prior notice.

【Packaging】

E-glass powder mat is packed in PE bags and put into cartons, stacked on pallets or separately put in cartons. Pallets should not be stacked over 2 layers and cartons not over 5 layers.

Roll width(mm)	roll weight(kg)	rolls/pallet	pallet size(mm)	weight per pallet(kg)
1270	52	6/9/12	1280*960	312/468/624
1400	42	8/12/20	1120*1420	336/504/840
1400	56	6/9/12	1280*960	336/504/672

【Storage】

This product should be stored in a dry, cool and rainproof place, with temperature from 5°C to 35°C and humidity between 35% and 65%. It is recommended to be used at room temperature, and finished within 12 months after receipt by customer and kept in intact package when not used to avoid damp.

地址：中国山东泰安市经济开发区

Add: Economic Development Zone, Taian, Shandong P.R.China

电话/Tel: +86 538 6622011

传真/Fax: +86 538 6627917

邮箱/E-mail: ctgf@ctgf.com

网址/Website: www.ctgf.com