

## TECHNICAL DATASHEET

SAP No. 30005112 Article Description X-S-E-860g/m<sup>2</sup>-1270mm

Textile Structure 7005514 SAERTEX®

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
5	CSM	250 g/m <sup>2</sup>	+/- 10.0 %	E-glass
4	45 °	301 g/m <sup>2</sup>	+/- 5.0 %	E-glass 600 TEX
3	90 °	1 g/m <sup>2</sup>	+/- 5.0 %	E-glass 68 TEX
2	0 °	1 g/m <sup>2</sup>	+/- 5.0 %	E-glass 68 TEX
1	-45 °	301 g/m <sup>2</sup>	+/- 5.0 %	E-glass 600 TEX
Stitching		6 g/m <sup>2</sup>	+/- 1 g/m <sup>2</sup>	PES [Polyester] 76 dtex

Fiber input can be determined individually

### FURTHER CHARACTERISTICS

Gauge	5.0	Stitching pattern	tricot	Width (nominal)	1,270 mm
Stitch length	2.60 mm	Total tolerance	6.5 %	Total areal weight	860 g/m <sup>2</sup>

**Labelling (Standard)** Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

**Packaging (Standard)** Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

**Storage** With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.