



## TECHNICAL DATASHEET

SAP No. 30004184 Article Description Y-E-1136g/m<sup>2</sup>-1270mm

Textile Structure 7004722 SAERTEX®

### ARTICLE CONSTRUCTION (in accordance with EN 13473-1)

Layer	Construction	Areal weight	Tolerance	Material
3	0 °	390 g/m <sup>2</sup>	+/- 5,0 %	E-glass 1.100 TEX
2	45 °	367 g/m <sup>2</sup>	+/- 5,0 %	E-glass 600 TEX
1	-45 °	367 g/m <sup>2</sup>	+/- 5,0 %	E-glass 600 TEX
Stitching		12 g/m <sup>2</sup>	+/- 3 g/m <sup>2</sup>	PES [Polyester] 76 dtex

Fiber input can be determined individually

### FURTHER CHARACTERISTICS

Gauge	10,0	Stitching pattern	tricot-warp	Width (nominal)	1.270 mm
Stitch length	2,60 mm	Total tolerance	+/- 5,2 %	Total areal weight	1136 g/m <sup>2</sup>

Tracer yarn<sup>1</sup> 7 PC yellow & tracer yarn 7 PC light green

<sup>1</sup>Position can be determined individually

**Labelling (Standard)** Every roll is equipped with a label in the core. A further label is located outside on the foil or on the box.

**Packaging (Standard)** Every roll is wound on a cardboard core and wrapped in foil. Further packaging options can be determined individually.

**Storage** With original packaging: No moisture recommendation and direct sunlight. To avoid problems with humidity and electrostatic charge, fabrics to be conditioned 24 hours prior to processing, independent of storage conditions.