



**Your Formula for Success**  
RESINS | GEL COATS | COLORANTS

## FIREPEL® K130 SERIES POLYESTER RESIN



# Product Information

## POLYESTER RESIN FOR FIRE RETARDANT APPLICATIONS

### Typical Cast Mechanical Properties<sup>1</sup>

Test	Unit of Measure	Nominal	Test Method
Tensile Strength	psi/MPa	10,700/73.8	ASTM D638 / ISO 527-1
Tensile Modulus	psi/GPa	580,000/4.0	ASTM D638 / ISO 527-1
Tensile Elongation	%	2.2	ASTM D638 / ISO 527-1
Flexural Strength	psi/MPa	15,400/106	ASTM D 790 / ISO 178
Flexural Modulus	psi/GPa	590,000/4.1	ASTM D 790 / ISO 178
Heat Distortion Temp.	°F/°C @264 psi	194/90	ASTM D648 / ISO 75-A
Barcol Hardness		45	ASTM D2583 / EN 59

### Typical Liquid Properties<sup>2</sup>

VERSIONS	Viscosity cps	Thix Index	Gel Time Min	Gel to Peak Min	Peak Exotherm (°F/°C)	Specific Gravity	Styrene Content, %
K130-72	825 <sup>1</sup>	NA	5 <sup>2</sup>	7	375/190	1.51	28
K130-LCS-00	450 <sup>3</sup>	NA	UV Cured	UV Cured	UV Cured	1.32	32
K130-NNP-08	150 <sup>9</sup>	NA	8 <sup>10</sup>	9	338/170	1.28	34
K130-NNT-00	200 <sup>3</sup>	NA	15 <sup>6</sup>	9	350/177	1.29	34
K130-PTA-15	375 <sup>3</sup>	3	15 <sup>5</sup>	9	347/175	1.29	33
K130-PTB-20	600 <sup>3</sup>	3 <sup>4</sup>	20 <sup>5</sup>	10	338/170	1.3	32
K130-PTE-12	550 <sup>3</sup>	3 <sup>4</sup>	12 <sup>5</sup>	10	374/190	1.29	33
K130-P TJ-15	425 <sup>3</sup>	2.5	15 <sup>5</sup>	12	320/160	1.29	33
K130-P TJ-20	400 <sup>3</sup>	2 <sup>4</sup>	20 <sup>5</sup>	9	350/177	1.29	34
K130-P TJ-45	450 <sup>3</sup>	2	45 <sup>8</sup>	10	320/160	1.29	33
K130-PTL-20	575 <sup>9</sup>	3	20 <sup>5</sup>	13	320/160	1.28	32
K130-PTO-15	375 <sup>3</sup>	3	15 <sup>5</sup>	9	347/175	1.29	33

NA—Not Applicable

- 77 °F/25 °C Brookfield RV viscosity spindle #3 at 20 rpm
- 180 °F/82 °C SPI Gel with 1.0% BPO
- 77 °F/25 °C Brookfield RV viscosity spindle #2 at 20 rpm
- 2/20 rpm Thix Index
- 77 °F/25 °C Gel time with 1.25% DDM-9
- 77 °F/25 °C Gel time with 0.25% Cobalt 6% & 1.25% DDM-9
- 77 °F/25 °C Gel time with 0.2% Cobalt 1.2% & 0.1% DEA
- 77 °F/25 °C Gel time with 2.0% DDM-9
- 77 °F/25 °C Brookfield LV Viscosity spindle #3 at 60 rpm
- 77 °F/25 °C Gel time with 1.5% DDM-9

### Flammability Properties (ASTM E-84 Tunnel Test)\*\* , \*\*\*

Laminate Construction <sup>1</sup>	ASTM E 84		UL 94			ASTM D2863 Limited Oxygen Index
	Flame Spread/Smoke Development <sup>2</sup>	HB Rating	V-o Rating	5V Rating		
1 ply 1.5 oz	25/135	PASS	PASS	PASS		
2 ply 2.0 oz	15/650					39
7 ply 1.5 oz	20/800					

- Laminates were 30-32 percent glass and post cured for 3 hours at 212 °F/100 °C.
- Smoke development of less than 450 is required for Class 1 rating.

### DESCRIPTION

Firepel K130 series resins are designed for fire resistant applications where ASTM E 84 Class I flame is required. Flammability of composite parts is dependent on the geometry of the part, degree of cure, reinforcement content, types of reinforcement, etc. It is the end user's responsibility to ensure that finished parts meet the required specifications. Published flammability properties should be used for comparison purposes only.

Firepel K130-72 is the concentrated highly brominated base resin that is used to manufacture the other versions.

### APPLICATION

Suitable for various fabricating methods such as hand lay-up, spray-up, filament winding, etc.

### BENEFITS

#### Fire Retardant

Firepel K130 PT, NN and TT series meet ASTM E 84 Class I flame spread requirements without the addition of fillers or antimony.

Certain laminate constructions can meet Class I smoke requirements. See "Flammability Property Table".

#### Low VOC

All Firepel K130 versions contain less than 35% styrene.

#### Versatile

The Firepel K130 series molecular architecture provides an excellent balance of fire retardant, physical properties and cost.

\*\* The degree of fire resistance of a cured resin is characterized by the ASTM E 84 test. This test is performed under strictly controlled conditions where a flame spread rating is assigned according to comparisons with test set-point materials. The behavior of the end-users composite cured under controlled condition can vary significantly in an actual fire situation due to the large number of unpredictable variables associated with actual fire situations.

\*\*\*Tests on K130-PT, NN and TT

Typical properties are not to be construed as specifications.

# FIREPEL®

## K130 SERIES POLYESTER RESIN



### PERFORMANCE GUIDELINES

A. Keep full strength catalyst levels between 1.0% - 2.0% of the total resin weight.

B. Maintain shop temperatures between 65°F/18°C and 90°F/32°C and humidity between 40% and 90%. Consistent shop conditions contribute to consistent gel time and will help the fabricator make a high quality part.

### STORAGE STABILITY

This product is stable for three months from the date of manufacture when stored in the original containers, away from direct sunlight or other UV light sources and at or below 77°F/25°C.

After extended storage, some drift may occur in the product viscosity and gel time.

### SAFETY

See the appropriate Material Safety Data Sheet for guidelines.

*Despite the general flame retardancy of this series of products, any laminate or other products made with fire retardant resins will burn if subject to an environment with a sufficient amount of heat and oxygen.*

### APPLICATION GUIDELINES

A. Halogen containing resins are generally less resistant to UV light than general purpose resins. Fabricators are advised to conduct their own tests to determine the suitability of using Firepel K130 Series resins for outdoor applications.

B. Due to the curing characteristics of the Firepel K130 Series resins, it is desirable to complete all secondary bonding as soon as possible. Exposure of the laminate to sunlight will result in severe secondary bonding, especially if the surface of the laminate has been allowed to become resin rich. Low fiberglass content and resin puddling should be avoided with this product. To assure adequate bonding to gel coats, fabricators should pre-wet the gel coat surface with a thin pass of catalyzed resin prior to lamination.

C. Chemical resistance studies have indicated the dicyclopentadiene resins such as Firepel K130 Series resins have inferior resistance to certain hydrophobic liquids such as hydrocarbons. Fuel storage tanks should not be produced with the Firepel K130 Series resins.

If your manufacturing needs require a more corrosion resistant resin, please contact your AOC representative for information or technical assistance on AOC's line of isophthalic or vinyl ester resins.

### ISO 9001:2008 CERTIFIED

The Quality Management Systems at every AOC manufacturing facility have been certified as meeting ISO 9001:2008 standards. This certification recognizes that each AOC facility has an internationally accepted model in place for managing and assuring quality. We follow the practices set forth in this model to add value to the resins we make for our customers.

### FOOTNOTES

(1) Based on tests of Firepel K130 base resin at 77°F/25°C and 50% relative humidity. All tests performed on unreinforced cured resin castings. Thixotropic components, if applicable are excluded from casting samples. Castings prepared using 1.0% MEKP, 0.10% Cobalt 12%, post cured for 5 hours at 212°F/100°C.

(2) The gel times shown are typical but may be affected by catalyst, promoter, inhibitor concentration, resin, mold, and shop temperature. Variations in gelling characteristics can be expected between different lots of catalysts and at extremely high humidities. Pigment and/or filler can retard or accelerate gelation. It is recommended that the fabricator check the gelling characteristics of a small quantity of resin under actual operating conditions prior to use.



Your Formula for Success  
RESINS | GEL COATS | COLORANTS

**AOC World Headquarters**  
955 Highway 57 East, Collierville, TN 38017

+01 901.854.2800

[AOC-Resins.com](http://AOC-Resins.com)

Pub. K130 SERIES NA  
Effective Date: April, 2017  
Copyright © 2017

### SALES CONTACTS

#### NORTH AMERICA

Toll free: +1 866 319 8827  
[northamerica@aoc-resins.com](mailto:northamerica@aoc-resins.com)

#### LATIN AMERICA

+01 863 815 5016  
[latinamerica@aoc-resins.com](mailto:latinamerica@aoc-resins.com)

#### MIDDLE EAST

+44 1206 390415  
[middleeast@aoc-resins.com](mailto:middleeast@aoc-resins.com)

#### EUROPE

+44 1206 390415  
[europa@aoc-resins.com](mailto:europa@aoc-resins.com)

#### AOC UK LTD.

+44 01206 390400  
[salesUK@aoc-resins.com](mailto:salesUK@aoc-resins.com)

#### INDIA

+44 1206 390415  
[india@aoc-resins.com](mailto:india@aoc-resins.com)

#### ASIA/AUSTRALIA

+44 1206 390415  
[asia@aoc-resins.com](mailto:asia@aoc-resins.com)

AOC is a registered trademark of AOC, LLC.

The information contained in this data sheet is based on laboratory data and field experience. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume any liability for occurrences arising out of its use. The user, by accepting the products described herein, agrees to be responsible for thoroughly testing each such product before committing to production. Our recommendations should not be taken as inducements to infringe any patent or violate any law, safety code or insurance regulation. This data sheet and its contents are the confidential and proprietary information of AOC and it may not be modified altered deconstructed or presented in any other manner without the explicit authorization of AOC and/or its legal counsel.